


# RESISTANCE CHART

*technology and quality*



---

**tubithor** S.p.A. 20050 LESMO (Mi) - Via Caduti per la Patria 83 - phone ( 39 ) 60.64.616 - Fax ( 39 ) 60.65.733

**thorsud** S.p.A. 66020 SAN SALVO (Ch) - Zona Industriale - phone ( 873 ) 54.96.47 - Fax ( 873 ) 34.12.38

[www.thorspa.com](http://www.thorspa.com) [sales@thorspa.it](mailto:sales@thorspa.it)

# ***RESISTANCE CHART***

This chart is designed to help You to select the proper hose to conduct the many materials found in industry.

It should be used as a **guide** because the resistance of a tube compound with a material depends on many variables:

- Temperature
- Concentration
- Pressure
- Velocity
- Duration of exposure
- Stability of the fluid
- Operating conditions

Also variations in elastomer types and their compounding for **specific service conditions** play an important part in the life of the hose.

When in doubt it is always advisable to contact our **Technical Service** for a recommendation.

The most commonly used materials are listed here.

Products not described or those outside of indicated conditions should be referred to us.

Ratings are for **concentrated** or **saturated** solutions at room temperature ( 21°C ) unless otherwise specified.

The rating code indicates the degree or range of serviceability for each type of hose.

## **RATING CODES**

**E : EXCELLENT**

Little or no effect on tube  
Suitable for continuous service

**G : GOOD**

Limited effect on tube. Generally suitable for continuous service and for intermittent use

**F : FAIR**

Moderate to severe effect on tube  
Not recommended for continuous service  
Generally suitable for intermittent use

**= : UNSUITABLE**

Not recommended

**BLANK**

Not enough data to determine an accurate rating


# ***RESISTANCE CHART***

## **WARNING**

- Many materials should be recognized as hazardous due to their characteristics and proper precautions must be taken in order to assure safe use. It is user's exclusive responsibility to develop suitable techniques; failure to take proper precautions could lead to serious bodily injury or property damage.
  
- Many chemicals which have little or limited effect on tube, if conveyed separately, can seriously reduce its suitability when carried together.
  
- Service conditions outside of described recommendations reduce considerably the ability of a particular compound to resist a material; in this case a practical test only can determine if the hose can fulfill its intended purpose.
  
- Chemical resistance does not imply conformance to the F D A or Europeans specifications when carrying products which may be used as foodstuffs or potable liquid. Nor does it imply non-staining characteristics in the case of chemicals.
  
- The Rating Codes are related to the tube only; in no case they can be taken in consideration with regard to the cover. Applications involving the resistance of the cover to a given product should be referred to our Technical Department.
  
- The reinforcement of the hose does never be in contact with the medium to be carried; in that case a capped ends hose must be used.
  
- Fittings and couplings assembling must be performed only by trained personnel. Great care should be taken for cross-linked polyethylene which above 38°C starts becoming soft from temperature alone.




# RESISTANCE CHART

		EPDM			NBR1			CSM			FPM			XLPE			UHMWPE																		
		TEMPERATURE °C																																	
		21			65			76			21			65			76			21			38			65			21			65			76
Air		E	G		E	G		E	G		E	G		E	E	G	E	E																	
Alabaster	Aq	E			E			E			E			E			E																		
Aliphatic Acid		E			E			E			E			E			E																		
Aliphatic Alcohols		Refer to a specific one																																	
Alk-Tri®		=			=			=			E			F			G	=																	
Alkil Benzene	Aq	=			=			=			E			E			E	=																	
Alkil Lauryl Sulphonate		E			E			G			E			E			E																		
Allyl Alcohol		E			E			E			E			E			E	E																	
Allyl Benzol		=			=			=			E			E			E	=																	
Allyl Bromide					=			=			G			G			G																		
Allyl Chloride		=			=			=			G			G			G	=																	
Alum	Aq	E	G		E	G		E	G		E			E	E	G	E	E																	
Aluminium Acetate	Aq	E			E			E			E			E			E	E																	
Aluminium Bromide		E			E			E			E			E			E																		
Aluminium Chlorate	Aq	E			E			E			E			E			E																		
Aluminium Chloride	Aq	E	G		E	G		E	G		E	G		E	E	G	E	E																	
Aluminium Fluoride		E	G		E	G		E	G		E			E	E	G	E	E																	
Aluminium Fluorosilicate		E			E			G			E			E			E																		
Aluminium Formate	Aq	F	=		=			G			=			E			E	E																	
Aluminium Hydroxide	Aq	E	G		E			F			E			E	E		E	E																	
Aluminium Iodide		E			E			G			E			E			E																		
Aluminium Nitrate	Aq	E			E			E	G		E			E			E																		
Aluminium Oxyde	Aq	E			E			E			E			E			E																		
Aluminium Phosphate	Aq	E			E			E			E			E			E																		
Aluminium Salts		Refer to a specific one																																	
Aluminium Sulphate	Aq	E			E			E	G		E			E	E	G	E	E	G																
Aluminium Sulphide		G			E			E			E			E			E	E																	
Aminobenzene		=			F						=			E			E																		
Aminodiethyle		F			=						=			E			E																		
Aminoethanol		E			F			G			=			E			E																		
Aminopropanol		G			F			=			=			E			E																		
Aminoethanol Amine		E			G			E			=			E			E																		
Aminoethyl Ethanolamine		E			F			G			=			E			E																		
Ammonia Anhydrous		Use Anhydrous Ammonia Hose Only																																	
Ammonia Gas		E	G		E			E			=			E			E	E																	
Ammonia Liquid	25	E	G		G			F			E	F		E			E																		
Ammonia Vapour		Use Anhydrous Ammonia Hose Only																																	
Ammonia Water	25	E	G		E			E	G	G	E	F		E	G		E	E																	
Ammonia Cupric Sulphate		=			E			E			E			E			E																		
Ammoniated Latex		=			G			F	=		E			E			E																		
<b>Corrosiv/ac</b>		<b>Corrosiv/spac</b>																																	
<b>Carbopomp/1tn</b>		<b>Nafta/16 1tn-tml-tmc</b>																																	
<b>Corrosiv/hyp</b>		<b>Corrosiv/spl hyp</b>																																	
<b>Corrosiv/viton</b>		<b>Corrosiv/spl viton</b>																																	
<b>Corrosiv/cl</b>		<b>Corrosiv/spcl</b>																																	
<b>Superior hbb</b>		<b>Superior/c hdn</b>									<b>Superior/spl hbb-hdn</b>																								


**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data

# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE			
	TEMPERATURE °C																		
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65	76
Ammonium Acetate	Aq	E			E			E			E			E			E	E	
Ammonium Alum		E			E			E			E			E			E	E	
Ammonium Bichromate								G									E	E	
Ammonium Biphosphate	Aq	E			E			E			E			E			E	E	
Ammonium Bisulphate	50	E			G			E			E			E			E	E	
Ammonium Bisulphite		G						G									E	E	
Ammonium Bromide	Aq	E			E			E			E			E			E	E	
Ammonium Carbamate								G											
Ammonium Carbonate	Aq	E			E	G		E			E			E			E	E	
Ammonium Chloride	Aq	E	G		E	G		E	G		E	G		E	E	G	E	E	G
Ammonium Chromate		E						G									E	E	
Ammonium Hydroxide	25	E	G		E			E	G	G	E	F		E	G		E	E	
Ammonium Methaphosphate	Aq	E	G		E	G		E	G		E			E	E	G	E	E	G
Ammonium Nitrate	Aq	E	G		E	G		E	G		E			E	E	G	E	E	
Ammonium Nitrite	Aq	E			E			E						E			E	E	
Ammonium Oxalate		E						G									E	E	
Ammonium Persulphate	Aq	G			F			E			E			E			E	E	
Ammonium Phosphate	Aq	E	G		E			E	G		E			E	E	G	E	E	G
Ammonium Stearate		E						G									E	E	
Ammonium Sulphate	Aq	E	G		E	G		E	G	G	E			E	E		E	E	G
Ammonium Sulphide	Aq	G	=		E	G		E	G		E			E	E	G	E	E	G
Ammonium Sulphite		E	=		E	G		E	G		E			E	E	G	E	E	
Ammonium Sulfocyanide		E	G		E	G		E	G		E			E	E	G	E	E	
Ammonium Thyocyanate	Aq	E	G		E	G		E	G		E			E	E	G	E	E	
Ammonium Thyocyanide	Aq	E			E						E			E			E	E	
Ammonium Thyosulphate	Aq	E			E			E			E			E	E	G	E	E	
Amyl Acetate		E			=			=			=			E	G		E	E	
Amyl Acetone		F			=			=			=			E			E	E	
Amyl Alcohol		G			E			E	G	G	E	G	G	E	G		E	E	
Amyl Amine					F			F			=			E			E	E	
Amyl Borate		=			F			E			E			E			E	E	
Amyl Chloride		=			=			=			E			E			E	=	
Amyl Chloronapthalene		=			=			=			E			E			E		
Amyl Napthalene		=			=			=			E			E			E		
Amyl Oleate		E			E			=						E			E	E	
Amyl Phenol					=			=			E			E			E	E	
Amyl Phtalate		=			=			=			F			E			E	F	
Amylene Hydrate		G			E			E	G	G	E	G	G	E	G		E	E	
Anethole		=			=			=						G			G	E	
Aniline		G	F		=			=			G	F	=	E	G		E	E	
<b>Corrosiv/ac</b>		<b>Corrosiv/spac</b>																	
<b>Carbopomp/1tn</b>		<b>Nafta/16 1tn-tml-tmc</b>																	
<b>Corrosiv/hyp</b>		<b>Corrosiv/spl hyp</b>																	
<b>Corrosiv/viton</b>		<b>Corrosiv/spl viton</b>																	
<b>Corrosiv/cl</b>		<b>Corrosiv/spcl</b>																	
<b>Superior hbb</b>		<b>Superior/c hdn</b>												<b>Superior/spl hbb-hdn</b>					


**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data

# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE		
	TEMPERATURE °C																	
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65
Aniline Chlorohydrate	G			=			=			G			E			E	E	
Aniline Dyes	F			=			=			G			E			E	E	
Aniline Hydrochloride	G			=			=			G			E			E	E	
Aniline Paint Oil ( low )	F			=			=						G			G	E	
Animal Fats	E			E			=			E			E			E	E	
Animal Grease	E			E			=			E			E			E	E	
Animal Oils				E			=			E			E			E	F	
Anone	F			=			=			=			E			E	F	
Antichlorine	E			E			E	G		E			E	E	G	E	E	G
Antifreeze	E	G		E	G		E	G	G	E	E	G	E	E	G	E	E	E
Antimony Chloride	50			E						E			E			E	E	
Antimony Pentachloride	Aq			E			=						G			E	E	
Aqua Regia	=			=			=			G			=			=		
Aromatic Alcohols				F														
Aromatic Amine	=			=			=			=			E			E		
Aromatic Hydrocarbons	40			E			=			E			E			E	E	
Aromatic Hydrocarbons	60			G			=			E			E			E	E	
Aromatic Hydrocarbons	99			=			=			G			G			G		
Aromatic Tar	=			F			=						E					
Aro-Tox®	=			F			=											
Arquads				E			E			E			E					
Arsenic Acid	E			E			E			E			E			E		
Arsenic Chloride				E			=			=			=			=		
Arsenic Trichloride				E			=			=			=			=		
Asphalt	=			E	G		G	F		E	E	G	G	F	=	E	=	=
ASTM 1 Oil	=			E			E			E			E			E	F	
ASTM 2 Oil	=			E						E			E			E		
ASTM 3 Oil	=			E						E			E			E		
Azote Gas	E			E	G		E			E			E			E	E	
Barium Acetate	G						G			G						E	E	
Barium Carbonate	Aq	E	G	E	G		E	G		E			E	E	G	E	E	
Barium Chloride	Aq	E	G	E	G		E	G		E			E	E	G	E	E	
Barium Chromate							G			G						E		
Barium Cyanide							G			G						E		
Barium Hydrate	Aq	E	G	E	F		E	G	G	E			E	E	G	E	E	E
Barium Hydroxide	Aq	E	G	E	F		E	G	G	E			E	E	G	E	E	E
Barium Fluoride				E			G			E			E			E		
Barium Nitrate				E			E			E			E			E		
Barium Oxyde				E			G			E			E			E		
Barium Peroxide				E			G			E			E			E		
<b>Corrosiv/ac</b> <span style="margin-left: 150px;"><b>Corrosiv/spac</b></span>																		
<b>Carbopomp/1tn</b> <span style="margin-left: 150px;"><b>Nafta/16 1tn-tml-tmc</b></span>																		
<b>Corrosiv/hyp</b> <span style="margin-left: 250px;"><b>Corrosiv/spl hyp</b></span>																		
<b>Corrosiv/viton</b> <span style="margin-left: 250px;"><b>Corrosiv/spl viton</b></span>																		
<b>Corrosiv/cl</b> <span style="margin-left: 350px;"><b>Corrosiv/spcl</b></span>																		
<b>Superior hbb</b> <span style="margin-left: 150px;"><b>Superior/c hdn</b></span> <span style="margin-left: 150px;"><b>Superior/spl hbb-hdn</b></span>																		


**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data

# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE			
	TEMPERATURE °C																		
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65	76
Barium Salts	Aq	E	G		E	G		E	G					E	E		E	E	
Barium Stearate		E			E			G			E			E			E		
Barium Sulphate	Aq	E			E	G		E			E			E			E		
Barium Sulphide	Aq	E	G		E	G		E	G		E	G		E	E	G	E	E	
Beet Sugar Liquors		E			E			E			E			E	E	G	E	E	
Belt Oil		=			G									E					
Benzaldehyde	Aq	F			=			=			=			E			E	F	
Benzal Chloride		=			=			=						E			E		
Benzene		=			=			=			E	G		E	G	=	E	G	=
Benzene Sulphonic Acid	10	F			=			E			E			E			E		
Benzene Trichloride		=			=			=			E			E			E		
Benzine Petroleum Ether		=			E			=			E			E			E		
Benzine Petroleum Naphta		=			E			=			E			E	G		E		
Benzine-Benzol-Ethanol (50-30-20)		=			=			=						E	G		E		
Benzine-Benzol (50-50)		=			E			=			E			E			E		
Benzo-o-Dicarboxylic Acid		E			E			E			E			E			E		
Benzoic Acid	Aq	E			E			G			E			E			E	E	
Benzoic Aldehyde					=			=			=			E			E		
Benzoic Acid Aldehyde		F			=			=			F			E					
Benzoic Acid Benzylester		F			=			=			F			E					
Benzoic Acid Ethylester					=			=			G			E			E		
Benzoic Acid Methylester		G			=			=			=			E			E		
Benzol		=			=			=			E	G		E	G	=	E	G	=
Benzophenol		=			=			=			E	G	G	E	G	F	E	G	
Benzophenone		F			=			=			E	F		E					
Benzotrichloride					=			=						G			G		
Benzoyl Chloride		=			=			=			G			G			E		
Benzyl Acetate		F			=			=			=			E			E		
Benzyl Acrylate		F			=			=			=			E					
Benzyl Alcohol					=			G			E			E			E	E	
Benzyl Benzoate		=			=			=			E			E					
Benzyl Chloride		=			=			=			E			E			E		
Benzylidene Chloride		=			=			=						E			E		
Bichromate of Soda	20	G			=			E	G	G	E			E	E	G	E		
Bismuth Carbonate	Aq	E			E			F			E			E					
Bitter Almonds Oil		F			=			=			=			E			E	F	
Black Sulphate Liquor		E			G	F		G	F		E			E	E	G	E		
Blast Furnace Gas		=			=			=			E			E	G		E	G	
Bleach		E			=			F			G			G			G		
Borax	Aq	E			E			E	G	G	E			E	G		E	E	
<b>Corrosiv/ac</b>		<b>Corrosiv/spac</b>																	
<b>Carbopomp/1tn</b>		<b>Nafta/16 1tn-tml-tmc</b>																	
<b>Corrosiv/hyp</b>		<b>Corrosiv/spl hyp</b>																	
<b>Corrosiv/viton</b>		<b>Corrosiv/spl viton</b>																	
<b>Corrosiv/cl</b>		<b>Corrosiv/spcl</b>																	
<b>Superior hbb</b>		<b>Superior/c hdn</b>												<b>Superior/spl hbb-hdn</b>					


**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data

# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE					
	TEMPERATURE °C																				
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65	76		
Bordeaux Mixture	E			G			E			E			E			E			E		
Boric Acid	E			E	G		E	G	G	E			E	G		E	E		E	E	
Brine	E			E	G		E	G		E			E	E		E	E		E	E	G
Bromine	=			=			=			G			=			=			=		
Bromine Trifluoride	=			=			=			=			=			=			=		
Bromine Water	G			=			E			E			E			=			E		
Bromobenzene	=			=			=			E			E			=			=		
Bromochloroethane	=			=			=			E			E			=			=		
Bromochloromethane	=			=			=			E			E			=			=		
Bromotoluene	=			=			=			E			E			=			=		
Bunker Fuel Oil	=			E			=			E			E	G		E	E		E	E	
Butadiene	=			F			=			E			E			E	E		E	E	
Butane Gas	=			E			E			E			E			E	E		E	E	
Butane Liquid	=			E			E			E			E			E	E		E	E	
Butane-Propane	Use Butane-Propane hose																				
Butanol	E			E			E			E			E	G		E	E		E	E	
Butanol Acetate	F			=			=			=			E			E	E		E	E	
Butene	F			E			E			E			E	G		E	E		G	E	F
Butyl Acetate	F			=			=			=			=			E	E		E	E	F
Butyl Acetoacetate	F			=			=			=			=			E	E		E	E	F
Butyl Acrylate	=			=			=			=			=			G	E		E	E	F
Butyl Alcohol	E			E			E			E			E	G		E	E		E	E	
Butyl Aldehyde	G			=			=			=			=			E	E		E	E	
Butyl Amine	=			F			=			G			E			E	E		E	E	
Butyl Benzene	=			=			=			E			E			E	E		E	E	
Butyl Benzoate	G			=			=			=			E			E	E		E	E	
Butyl Bromide	=			=			=			G			=			E	E		E	E	
Butyl Butyrate	=			=			=			=			=			G	E		G	E	F
Butyl Carbitol	E			G			G			E			E			E	E		E	E	
Butyl Cellosolve	E			E			E			E			E			=	E		E	E	
Butyl Chloride	=			F			=			E			E	G		E	E		E	E	
Butyl Diglycol	E			E			=			E			E			=	E		E	E	
Butyl Ether	=			=			=			=			=			E	E		E	E	=
Butyl Glycol	E			E			E			E			E			=	E		E	E	
Butyl Mercaptan	=			=			=			E			E			F	E		E	E	
Butyl Oleate	G			=			=			E			E			E	E		E	E	
Butyl Phtalate	=			=			=			F			E			E	E		E	E	F
Butyl Stearate	F			=			=			E			E			E	E		E	E	
Butyl Acetyl Recinoleate	=			=			=			=			=			E	E		E	E	
Butyl Benzyl Phtalate	F			=			=			F			E			E	E		E	E	
<b>Corrosiv/ac</b>			<b>Corrosiv/spac</b>																		
<b>Carbopomp/1tn</b>			<b>Nafta/16 1tn-tml-tmc</b>																		
<b>Corrosiv/hyp</b>			<b>Corrosiv/spl hyp</b>																		
<b>Corrosiv/viton</b>			<b>Corrosiv/spl viton</b>																		
<b>Corrosiv/cl</b>			<b>Corrosiv/spcl</b>																		
<b>Superior hbb</b>			<b>Superior/c hdn</b>									<b>Superior/spl hbb-hdn</b>									


**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data

# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE					
	TEMPERATURE °C																				
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65	76		
Butyl Diethylene Glycol	E			E			=			E			E			E					
Butyl Diglycol Acetate	E			=			=			=			=			E			E		
Butyl Ethyl Acetaldehyde	F			=			=			=			=			F			F		
Butyl Ethyl Ether				=			=			=			=			E			E		
Butyl Glycol Acetate	E			=			=			=			=			E			E		
Butyl Monobutylether	E			F						F						E					
Butylene	F			E			E			E			E			G			G		
Butyraldehyde	G			=			=			=			=			E			E		
Butyric Acid	Aq F			=			F			E			E			E			E	F	
Butyric Acid Ethylester	E			=			=			=			=			E			E		
Butyric Anhydride				=			G			=			F	=		F			F		
Cadmium Acetate	E			F			=			E			E			E			E		
Cadmium Cyanide	E						E			E			E			E			E		
Cadmium Salts	Refer to a specific one																				
Calcium Acetate	Aq G			E			G			G			G			E			E		
Calcium Aluminate	E			E			E			E			E			E			E		
Calcium Arsenate	E			E			G			E			E			E			E		
Calcium Bicarbonate	E			E			G			E			E			E			E		
Calcium Bichromate	E						G	F	=				E	G	G	E	G	G	E	G	G
Calcium Biphosphate	E			E			G			E			E			E			E		
Calcium Bisulphate	Aq E			E			E	G		E			E	E	G	E	E	G	E	E	G
Calcium Bisulphite	=			E	G		E	G	G	E			E	E	G	E	E	G	E	E	G
Calcium Bromide	E			E			G			E			E			E			E		
Calcium Carbonate	E			E			E	G		E			E	E	G	E	E	G	E	E	G
Calcium Chlorate	Aq E			E	G		E			E			E			E			E	E	
Calcium Chloride	Aq E			E	G		E	G		E			E	E	G	E	E	G	E	E	G
Calcium Chromate	G						G												E		
Calcium Fluophosphate	E			E			E			E			E			E			E		
Calcium Fluoride	E			E			G			E			E			E			E		
Calcium Hydroxide	Aq E	E	G	G	F		E	G	G	E			E	E	G	E	E	G	E	E	G
Calcium Hypochloride	Aq E			E						E			E			E			E		
Calcium Hypochlorite	5 G	G		=			E	G		E			E			E			E	E	
Calcium Hypochlorite	20 F	=		=			G	F		E	G		E	G		E			E	G	
Calcium Hypochlorite ( no free Chlorine )	E	G		F			E	G		E	G		E	G		E	E	G	E	E	G
Calcium Methaphosphate	E			E			G			E			E			E			E		
Calcium Nitrate	Aq E	G		E			E	G		E			E	E	G	E	E	G	E	E	G
Calcium Oleate	E			E			G			E			E			E			E		
Calcium Oxyde	G															E			E		
Calcium Phosphate	50 E			E			E			E			E			E			E	E	


**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data

# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE		
	%	TEMPERATURE °C																
		21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65
Calcium Salts	Refer to a specific one																	
Calcium Silicate	E			E			E	G		E			E	E	G	E	E	G
Calcium Stearate	E			E			G	G		E			E			E	E	
Calcium Sulphate	Aq	E	G	E	G		E	G		E			E	E	G	E	E	G
Calcium Sulphhydrate		E		E			E			E			E			E		
Calcium Sulphide	Aq	E		E			E	G		E			E	E	G	E	E	G
Calcium Sulphite				E			E	G		E			E	E	G	E	E	G
Caliche Liquors		E		E			E			E			E	G		E		
Cane Sugar Liquors	Aq	E		E			E			E			E	G		E	E	
Caprylic Acid		G		=			=			=			G			E		
Carbinol		F	=	F			E	G		E	G		E	G		E	E	
Carbitol		E		E			E			E			E			E		
Carbitol Acetate				=			=			=			E			E		
Carbolic Acid		=		=			=			E	G	G	E	G	F	E	G	
Carbon Bioxide, gaseous		G		E	G		G	G		E			E	G		E	E	
Carbon Bisulphide		=		=			=			E			E		F	F		
Carbon Monoxide, gaseous		=		E			F			E			E	E		E	E	G
Carbon Sulphide		=		=			=			E			E		F	F		
Carbon Tetrachloride		=		=			=			E	G		F		F	G		
Carbon Tetrafluoride ( Freon 14 )		=		=			=			E			E		E	E		
Carbonic Acid		E	E	E			E			E			E	G		E		
Casein		E		E			E			E			E			E		
Castor Oil		G		E			E	G		E			E	G		E	E	
Caustic Lime		G											E			E		
Caustic Potash	20	E	G	G			E	G	G	E	G	G	E	E	G	E	E	
Caustic Potash	50	E	G		=		G	G		G	G		E			E	E	
Caustic Soda	20	E	G	G	E	G	E	G		E			E			E		
Caustic Soda	40	G	G	G	=		E	G		E	G		E			E		
Caustic Soda	50	G	G	G	=		E	G		E			E			E		
Caustic Soda	70	=			=		E	G	G	=			E			E	E	
Cellosize®		G		=			=			=			E			E		
Cellosolve		G		=			=			=			E			E		
Cellosolve Acetate		G		=			=			=			E	G		E		
Cellulube Hydraulics Fluids				=			=						E			E		
Cellulose Acetate		G		=			=			E			E			E		
Cetylic Acid		G		E	F		F	=		E			G			E	E	
Cetylacetic Acid		E		E	F		G	F		E			E	G		E	G	
Chile Saltpetre		E	G	E			E	G		E	G		E	E	G	E	E	G
Chine Wood Oil		=		E			E			E			E	G		E	G	
Chlordane-Water ( 5%-95% )													E			E		
<div style="display: flex; justify-content: space-between;"> <span style="color: blue;"><b>Corrosiv/ac</b></span> <span style="color: blue;"><b>Corrosiv/spac</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span style="color: blue;"><b>Carbopomp/1tn</b></span> <span style="color: blue;"><b>Nafta/16 1tn-tml-tmc</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span style="color: blue;"><b>Corrosiv/hyp</b></span> <span style="color: blue;"><b>Corrosiv/spl hyp</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span style="color: blue;"><b>Corrosiv/viton</b></span> <span style="color: blue;"><b>Corrosiv/spl viton</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span style="color: blue;"><b>Corrosiv/cl</b></span> <span style="color: blue;"><b>Corrosiv/spcl</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span style="color: blue;"><b>Superior hbb</b></span> <span style="color: blue;"><b>Superior/c hdn</b></span> <span style="color: blue;"><b>Superior/spl hbb-hdn</b></span> </div>																		


**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data

# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE		
	TEMPERATURE °C																	
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65
Chlorylene	=			=			=			E			F			G	=	
Chlorinated Hydrocarbons	=			=			=						G			G		
Chlorinated Solvents Dry	=			=			=			E			E	G		E	G	
Chlorinated Solvents Wet	=			=			=			E			E	G		E	G	
Chlorine Bioxide	=			=			F			E			F			F		
Chlorine Gas Dry	F			=			G			G	G	F	=			F	=	
Chlorine Gas Wet	G			=			G			G	G		=			F	=	
Chlorine Water	3	G		=			G			G	G		E			E	F	
Chlorine Water Saturated		G		=						E						E	F	
Chloroacetic Acid	25	F		=			F			=			=			E	E	
Chloroacetone		E		=			=			=			E			E		
Chlorobenzene		=		=			=			E			E			E		
Chlorobenzol		=		=			=			E			E			E		
Chlorobromomethane		=		=			=			E			=			=		
Chlorobutadiene		=		=			=			E			E			E		
Chlorobutane		=		F			=			E			G			E		
Chlorocalcium	Aq	E		E	G		E	G		E			E	E	G	E	E	G
Chlorodifluoromethane		=		=			E			=			F			E		
Chloroethyle		=		=			=			E			G			G		
Chloroethylene		=		=			=			E			E			E	=	
Chloroethylbenzene		=		=			=			E			G			G		
Chlorohydrogen ( without water )		E		=			E			E			E			E		
Chloroform		=		=			=			E			F			F	=	
Chloronaphtalene		=		=			=			G								
Chloropentane		=		=			=			E			E			E		
Chlorophenol		F		=			=			G			G			G		
Chloropotassium	Aq	E		E	G		E	G		E			E	E		E	E	
Chloropropanone		=		=			=			=			E			E		
Chloroprene Monomer		=		=			F			=								
Chlorosulphonic Acid		=		=			=			=			F			F		
Chlorotene		=		=			=			E			E			E		
Chlorotoluene		=		=			=			G			G			G		
Chlorox®		=		=			E			E			G			E		
Chromate		G					G			G						E		
Chrome Alum	Aq						G			G						E	E	
Chrome Acetate							G			G						E		
Chrome Plating Solutions		G		=			=			=								
Chrome Salts																		
Chrome Sulphate		E					E			G			E			E		
Chromic Acid	10	E		=			E	G		E			E			E		
Refer to a specific one																		
Corrosiv/ac			Corrosiv/spac															
Carbopomp/1tn			Nafta/16 1tn-tml-tmc															
Corrosiv/hyp			Corrosiv/spl hyp															
Corrosiv/viton			Corrosiv/spl viton															
Corrosiv/cl			Corrosiv/spcl															
Superior hbb			Superior/c hdn						Superior/spl hbb-hdn									


**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data

# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE			
	%	TEMPERATURE °C																	
		21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65	76
Chromic Acid	25	F			=			E	G		E			E			E		
Chromic Acid	50	=			=			E	G		E			F			F	=	
Citric Acid, aqueous	30	E			E	G		E	G		E			E	G		E	E	
Coal Oil		=			E			=			E			E			E		
Coal Tar		=			E			G			E			G			E		
Coal Tar Naphta		=			F			=			E			E			E		
Cobalt		E			E			E			E			E			E		
Cobalt Chloride		E			E			E			E			E			E		
Cobalt Salts	Aq	E			E			E			E			E			E		
Cobalt-Nickel Plating Solutions														G			G		
Coconut Oil		=			E			F			E			E			E		
Cod Liver Oil		E			E			G			E			E			E	F	
Coke Oven Gas		=			F			E			E			F			F		
Coloradol®		=			=			=			E			E			E		
Compressor Oil		=			E			F			E			E			E		
Copper Acetate	Aq	E			F			G			E			E			E		
Copper Arsenale		E			E			E			E			E			E		
Copper Chloride	Aq	E	G		E	G		G	F		E	G		E	E	G	E	E	
Copper Cyanide	Aq	E			E	G		E			E			E			E		
Copper Fluoride	Aq	E			E			G			E			E			E	E	
Copper Hydrate		E			G			E			E			E			E		
Copper Hydroxide		E			G			E			E			E			E		
Copper Nitrate	Aq	E	G		E			E	G		E			E	E	G	E	E	
Copper Nitrite		E			E			E			E			E			E		
Copper Sulphate	Aq	E	G		E	G		E	G	G	E			E	E	G	E	E	
Copper Sulphide		E			E			E			E			E	G		E	G	
Copper Vitriol	Aq	E	G		E	G		E	G	G	E			E	E	G	E	E	
Core Oil																			
Corn Oil		=			E			G			E			E	G		E		
Cottonseed Oil		G			E			E			E	E	G	E	G		E	E	
Creosote ( Wood or Coal Tar )		=			G			=			E	E	G	E	G		E	F	
Cresol		=			F	=		=			E			E	G	F	F		
Cresol-Xylene ( 95%-5% )		=						=			E			E			E		
Cresol-Xylene-DDt ( 90%-5%-5% )		=						=			E			E			E		
Cresylic Acid		=			F	=		=			E			E	G	F	E		
Cresylic Alcohol		=			F	=		=			E			G	F	=	G		
Crotonaldehyde		F			=			=			E			E			E	F	
Crude Oil		=			E			=			E			E			E		
Cryolite	10	E			F	=		E			E			E			E		
Cumene		=			F			=			E			E			E		
<b>Corrosiv/ac</b>		<b>Corrosiv/spac</b>																	
<b>Carbopomp/1tn</b>		<b>Nafta/16 1tn-tml-tmc</b>																	
<b>Corrosiv/hyp</b>		<b>Corrosiv/spl hyp</b>																	
<b>Corrosiv/viton</b>		<b>Corrosiv/spl viton</b>																	
<b>Corrosiv/cl</b>		<b>Corrosiv/spcl</b>																	
<b>Superior hbb</b>		<b>Superior/c hdn</b>												<b>Superior/spl hbb-hdn</b>					

**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data

# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE					
	TEMPERATURE °C																				
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65	76		
Cuprammonium Sulphate	E			E			E			E			E			E			E		
Cupric Carbonate	E			G			G			E			E			E			E		
Cupric Chloride	E	G		E	G		G	F		E	G		E	E	G	E	E		E		
Cupric Cyanide	Aq	E		E	G		E			E			E			E			E		
Cupric Nitrate	E	G		E			E	G		E			E	E	G	E	E		E	E	
Cupric Nitrite	E			E			E			E			E			E			E		
Cupric Sulphate	E	G		E	G		E	G	G	E			E	E	G	E	E		E	E	
Cuprous Chloride	E									E			E			E			E		
Cuprous Cyanide	Aq	E								E			E			E			E		
Cyclobutane Oxide	=									=			=								
Cyclohexane	=			=			=			E			E			E			E	E	
Cyclohexanol	G			G			G			G			E			E			E	E	F
Cyclohexanone	F			=			=			=			E			E			E		F
Cyclohexene	=			=			=			E			E			E			E		
Cyclohexyl Amine	=			=			=			E			E			E			E		
Cyclopentane	=			=			=			E			E			E			E		
Cyclopentane Metyl	=			=			=			E			E			E			E		
Cyclopentanol	=			=			=			E			E			E			E		
Cyclopentanone	=			=			=			E			E			E			E		
Cymene	=			=			=			E			E			E			E		
DDT and Kerosene	=			=			=			E			E			E			E		
DDT in Solvent	Refer to Solvent																				
Decahydronaphtalene	=			=			=			G			F			G	F				
Dekalin	=			=			=			G			F			G	F				
Decane	=			E			=			E			E			E			E		
Decanol	G			E			=			E			E			E			E		
Decyl Alcohol	G			E			E			E			E			E			E		
Decyl Aldehyde				=			=			=			E			E			E		
Decyl Butyl Phtalate				=			=			=			E			E			E		
Denaturated Alcohol	E			E			E	G		E			E			E			E		
Diacetone	E			=			=			=			E			E			E		
Diacetone Alcohol	G			=			G			=			E			E			E		
Diamyl Amine				F			F						E			E			E		
Diamyl Naphtalene				=			=			F			E			E			E		
Diamyl Phenol				=			=			F			E			E			E		
Diamyl Phtalate	=			=			=			=			E			E			E		
Diamylene	=			=			=			=			E			E			E		
Dibenzyl Ether	F			=			=			=			E			E			E		
Dibenzyl Sebacate	G			=			=			E			E			E			E		
Dibromobenzene	=			=			=			E			E			E			E		
<b>Corrosiv/ac</b>			<b>Corrosiv/spac</b>																		
<b>Carbopomp/1tn</b>			<b>Nafta/16 1tn-tml-tmc</b>																		
<b>Corrosiv/hyp</b>			<b>Corrosiv/spl hyp</b>																		
<b>Corrosiv/viton</b>			<b>Corrosiv/spl viton</b>																		
<b>Corrosiv/cl</b>			<b>Corrosiv/spcl</b>																		
<b>Superior hbb</b>			<b>Superior/c hdn</b>									<b>Superior/spl hbb-hdn</b>									


**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data








# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE																			
	TEMPERATURE °C																																		
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65	76																
Ethyl Acetate	F			=			=			=				E			E																		
Ethyl Acetoacetate	G			=			=			=				E			E																		
Ethyl Acrylate	F			=			=			=				E			E																		
Ethyl Adipate	F			=			=			=																									
Ethyl Alcohol	G			G			E	G	G	E				E	G		E	E																	
Ethyl Aldehyde	E			=			=			=				E	E		E	E																	
Ethyl Amine	F			=			=			=				E			E																		
Ethyl Benzene	=			=			=			=				E			E																		
Ethyl Benzoate	E			=			=			=				E			E																		
Ethyl Benzol	=			=			=			=				E			E																		
Ethyl Bromide	E			F			=			=				F			F																		
Ethyl Butanol	E			E			E			E				E			E																		
Ethyl Butyrate	E			=			=			=				E			E																		
Ethyl Carbinol	G			G			E	G	G	E				E	G		E	E																	
Ethyl Cellulose	G			G			F			=				E	G		E																		
Ethyl Chloride	=			=			=			=				G			G																		
Ethyl Chloroacetate	E			=			=			=				E			E																		
Ethyl Dichloride	=			=			=			=				E			E	=																	
Ethyl Diglycol	E			E			E			E				E			E																		
Ethyl Ether	=			=			=			=				E			E	F																	
Ethyl Formate	G			=			=			=				E			E																		
Ethyl Glycol	E			E			E			E				E	G	=	E																		
Ethyl Hexanol	=			E			G			G				E			E	F																	
Ethyl Iodide	=			=			=			=				E			E																		
Ethyl Ketone	F			=			=			=				E			E																		
Ethyl Mercaptan	=			=			=			=				E			E																		
Ethyl Oxalate	=			=			=			=				E			E																		
Ethyl Phtalate	F			=			=			=				E			E																		
Ethyl Silicate	G			E			G			E				E			E																		
Ethyl Sulphate	=			=			=			=				E			E																		
Ethyl Aluminium Dichloride				=			=			=																									
Ethyl Butyl Acetate	G			=			=			=				E																					
Ethyl Butyl Alcohol	E			E			E			G				E			E																		
Ethyl Butyl Amine				F	=		F																												
Ethyl Butyl Ketone	=			=			=			=				E			E																		
Ethyl Butyraldehyde	G			=			=			=				E			E																		
Ethyl Glycol Acetate	E			=			E			E				E	G		E																		
Ethyl Hexoic Acid	=			=			=			=				E																					
Ethyl Hexyl Acetate	=			=			=			=				G																					
Ethyl Hexyl Alcohol	E			E			E			E				E																					
<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 33%;"><b>Corrosiv/ac</b></td> <td style="width: 33%;"><b>Corrosiv/spac</b></td> <td style="width: 34%;"></td> </tr> <tr> <td><b>Carbopomp/1tn</b></td> <td colspan="2"><b>Nafta/16 1tn-tml-tmc</b></td> </tr> <tr> <td><b>Corrosiv/hyp</b></td> <td colspan="2"><b>Corrosiv/spl hyp</b></td> </tr> <tr> <td><b>Corrosiv/viton</b></td> <td colspan="2"><b>Corrosiv/spl viton</b></td> </tr> <tr> <td><b>Corrosiv/cl</b></td> <td colspan="2"><b>Corrosiv/spcl</b></td> </tr> <tr> <td><b>Superior hbb</b></td> <td style="text-align: center;"><b>Superior/c hdn</b></td> <td style="text-align: right;"><b>Superior/spl hbb-hdn</b></td> </tr> </table>																		<b>Corrosiv/ac</b>	<b>Corrosiv/spac</b>		<b>Carbopomp/1tn</b>	<b>Nafta/16 1tn-tml-tmc</b>		<b>Corrosiv/hyp</b>	<b>Corrosiv/spl hyp</b>		<b>Corrosiv/viton</b>	<b>Corrosiv/spl viton</b>		<b>Corrosiv/cl</b>	<b>Corrosiv/spcl</b>		<b>Superior hbb</b>	<b>Superior/c hdn</b>	<b>Superior/spl hbb-hdn</b>
<b>Corrosiv/ac</b>	<b>Corrosiv/spac</b>																																		
<b>Carbopomp/1tn</b>	<b>Nafta/16 1tn-tml-tmc</b>																																		
<b>Corrosiv/hyp</b>	<b>Corrosiv/spl hyp</b>																																		
<b>Corrosiv/viton</b>	<b>Corrosiv/spl viton</b>																																		
<b>Corrosiv/cl</b>	<b>Corrosiv/spcl</b>																																		
<b>Superior hbb</b>	<b>Superior/c hdn</b>	<b>Superior/spl hbb-hdn</b>																																	

**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data




# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE		
	TEMPERATURE °C																	
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65
Fluorine	=			=			=			=			=			=		
Fluorobenzene	=			F			=			E			E			=		
Fluorolube®	G			E			E			E			E					
Fluosilicic Acid	G			=			E	G	G	E			E			E		
Fluosilicic Acid	50 G			=			E	G	G	E			E			G		
Formaldehyde, aqueous	40 G			F			G	=		G			E	G		E	E	
Formalin	30 G			F			G	=		G			E	G		E	E	
Formamide	E			G			G	=		=			E	G		E	E	
Formic Acid, aqueous	99 G	=		=			E	G		=			G	G		E	G	
Formic Acid, aqueous	10 E	G		G	=		E	G		E	G		E	G		E	E	
Formic Acid Dimethylamide	E			=						=			E					
Freon® 11	=			G			E			E			E			E		
Freon® 12	=			=			=			=			E			G		
Freon® 13				E									E			E		
Freon® 14	=			=									E			E		
Freon® 21				=									E			E		
Freon® 22	=			=			E			=			F			E		
Freon® 112	=			G						G								
Freon® 113	=			G			E			E								
Freon® 114	E			E			E			E			E			E		
Fuel Oil	=			E			=			E			E	G		E		
Fuel ASTM A ( Isooctane )	=			E			E			E			E			E	F	
Fuel ASTM B ( Isooctane 70%-Toluene 30% )	=			E			=			E			E			E		
Fuel ASTM C ( Isooctane 50%-Toluene 50% )	=			E			=			E			E			E		
Fuel ASTM 1 Oil	=			E						E			E			E		
Fuel ASTM 2 Oil	=			E						E			E			E		
Fuel ASTM 3 Oil	=			E						E			E			E		
Fumaric Acid				G			G			E						E		
Furan	=			=			=			=			E			E		
Furfural	F			=			G			=			E			E	F	
Furfurol	F			=			G			=			E			E	F	
Furfuryl Alcohol	F			=			G			=			E			E	F	
Furfuryl Aldehyde	F			=			G			=			E			E	F	
Fusel Oil				E						E			E			E		
Gallic Acid	G			=			G	F		G			E	E	G	E		
Gasoline 65 Octane	=			E			=			E			E			E		
Gasoline 100 Octane	=			E			=			E			E			E		
Gasoline Lead Free	=			E			=			E			E			E		
<b>Corrosiv/ac</b>			<b>Corrosiv/spac</b>															
<b>Carbopomp/1tn</b>			<b>Nafta/16 1tn-tml-tmc</b>															
<b>Corrosiv/hyp</b>			<b>Corrosiv/spl hyp</b>															
<b>Corrosiv/viton</b>			<b>Corrosiv/spl viton</b>															
<b>Corrosiv/cl</b>			<b>Corrosiv/spcl</b>															
<b>Superior hbb</b>			<b>Superior/c hdn</b>									<b>Superior/spl hbb-hdn</b>						

**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data

# RESISTANCE CHART


	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE			
	TEMPERATURE °C																		
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65	76
Gasoline Aviation	=			G			=			E			E			E			
Gelatine	Aq	E		E			E			E			E			E	E		
Genantin		E		E			E			E			E			E	E		
Glauber Salt	Aq	E	G	E	G		E	G		E			E	E	G	E	E	G	
Gluconic Acid		=		=			G			E			E			E			
Glucose	Aq	E	G	E	G		E	E	G	E			E	E	G	E	E	G	
Glue ( Animai )		E		E			E	G	G	E			E	E		E	E		
Glycerine		E		E	G		E	G	G	E	E	G	E	G		E	G		
Glycerol	Aq	E		E	G		E	G	G	E	E	G	E	G		E	E		
Glycol	Aq	E	G	E	G		E	G	G	E	G	G	E	G	=	E	E		
Glycol Acid	40	E		=			E			E			E			E	E		
Glycol Acid Butylester		E		=			=			E			E			E	E		
Glycol Acid Monoethyl Ether		E		=			=			=			E			E	E		
Glystantin		E		E			E			E			E			E	E		
Gypsum		E	G	E	G		E	G		E			E	E	G	E	E	G	
Grease		=		E			=			E			G			E			
Green Sulphate Liquor		E		E			E	G		G			E	E	G	E			
Ground Nut Oil		E		E			E			E			E			E	E		
Halowax® Oil		=		=			=			E			E			E	E		
Harness Oil		=											E			E			
Heptacor in Petroleum Solvents		=		F			=						E						
Heptaldehyde		=		=			=			=			E						
Heptanal		=		=			=			=			E						
Heptane		=		E			=			E			E			E	F		
Heptane Carboxylic Acid		=		F			G	=		=			E			E	E		
Hexadecanoic Acid		G		E	F		F	=		E			G			E	E		
Hexahydrobenzene		=		=			=			E			E			E	E		
Hexahydrophenol		G		G			G			G			E			E	E		
Hexaldehyde		F		=			=			=			E						
Hexaline		G		G			G			G			E			E	E		
Hexamethylene		=		=			=			E			E			E	E		
Hexane		=		E			G			E			E			E	E		
Hexene		=		G			=			E			E			E			
Hexanol		G	F	E			E	G		E			E			E			
Hexyl Alcohol		G	F	E			E	G		E			E			E			
Hexyl Amine		=		=			=			=			E			E			
Hexyl Methyl Ketone		=		=			=			=			E			E			
Hexylene				E			=			E			G			G			
Hexylene Glycol		E		E			E	G		E			E	E	G	E	E	G	
HI-Tri®		=		=			=			E			F			G	=		
<b>Corrosiv/ac</b>			<b>Corrosiv/spac</b>																
<b>Carbopomp/1tn</b>			<b>Nafta/16 1tn-tml-tmc</b>																
<b>Corrosiv/hyp</b>			<b>Corrosiv/spl hyp</b>																
<b>Corrosiv/viton</b>			<b>Corrosiv/spl viton</b>																
<b>Corrosiv/cl</b>			<b>Corrosiv/spcl</b>																
<b>Superior hbb</b>			<b>Superior/c hdn</b>									<b>Superior/spl hbb-hdn</b>							

**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data






# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE		
	TEMPERATURE °C																	
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65
Isotridecyl Alcohol	G			E			E	G	G	E			E			E		
Jet Fueis ( JP1 to JP5 )	=			E			=			E			E			E		
Kerosene	=			E	G	F	F			E	E	G	E	G		E	G	
Kerosene-Xylene ( 95%-5% )	=			=			=			E			E	G		E	G	
Ketones	F			=			=			=			E			E	F	
Lacquers	=			=			=			=			G			G		
Lacquer Solvents	Refer to solvent																	
Lactic Acid	G			E	=		E			E			E	G		E	E	
Lactic Acid, aqueous	50	G			E	=	E			E			E			E	E	
Lactol	=			=			=			E			E			E		
Lasso®	E			E			E			E			E			E		
Lauryl Alcohol				E			E			G			E			E		
Lavender Oil	=			G			=			E			E			E		
Lead Acetate	Aq	E			F		E			E			E			E	E	
Lead Arsenale	Aq	E			E		E			E			E			E		
Lead Nitrate	Aq	E	G		E		E	G		E			E			E		
Lead Sugar	Aq	E			F		E			E			E			E	E	
Lead Sulfamate		E			G		E			E			E			E		
Lead Sulphate	Aq	E	G		E	G	E	G		E	G		E	E	G	E	E	G
Lead Tetraethyle	=			=			=			E			E			E		
Light Oil Residual	=			E			=			E			E			E		
Ligroin	=			E			=			E			E			E		
Lime Water	E			=			G			E			E			E	E	
Lime Sulphur				=									E			E		
Lindane®	E			E									E			E		
Lindol	F			=			=			E			E			E		
Linoleic Acid				=						E			E			E		
Linseed Oil	G			G			E			E			E	G		E	E	
Liquid Soap	E	G	G	E			E	G		E			E			E	E	
Lithium Hydroxide	G			=			=			=			E			E		
L.P.G.	Use L.P.G. Hoses Only																	
Lubricating Oils	=			E			=			E			E			E		
Lye	20	E	G	G	E	G	E	G		E			E			E		
Magnesium Acetate		F			=		=			=			E			E		
Magnesium Bicarbonate		E			E		E			E			E			E		
Magnesium Carbonate	Aq	=			E	G	E			E			E			E	E	
Magnesium Chloride	Aq	G			E	G	E	G	G	E	G		E	E	G	E	E	
Magnesium Fluoride		E			E		G			E			E			E		
Magnesium Hydrate		G			G		G	F		G			E	E	G	E	E	G
Magnesium Hydroxide	Aq	E			G	F	E	G	G	E	G		E	E	G	E	E	
<div style="display: flex; justify-content: space-between;"> <span><b>Corrosiv/ac</b></span> <span><b>Corrosiv/spac</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span><b>Carbopomp/1tn</b></span> <span><b>Nafta/16 1tn-tml-tmc</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span><b>Corrosiv/hyp</b></span> <span><b>Corrosiv/spl hyp</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span><b>Corrosiv/viton</b></span> <span><b>Corrosiv/spl viton</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span><b>Corrosiv/cl</b></span> <span><b>Corrosiv/spcl</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span><b>Superior hbb</b></span> <span><b>Superior/c hdn</b></span> <span><b>Superior/spl hbb-hdn</b></span> </div>																		


**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data

# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE		
	TEMPERATURE °C																	
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65
Magnesium Lye	E						G			E			E			E		
Magnesium Nitrate	Aq	E	G		E		E	G		E	G		E	G		E	G	
Magnesium Oxide		E			E		G			E			E			E		
Magnesium Phosphate		E			E		E			E			E			E		
Magnesium Sulphate	Aq	E	G		E	G	E	G		E	G		E	E		E	E	
Magnesium Thyosulphate		E			E		G			E			E			E		
Magnesium Ammonium Sulphate		E			E		E			E			E			E		
Malathion 50% in Aromatic Solvents		=			=		=			E			E			E		
Maleic Acid	Aq	=			=		=			G			G			E	E	
Maleic Acid Anhydride		E			E		E			E			E			E		
Maleic Acid Diethylester		E			=		E			E			E			E	E	
Maleic Acid Dimethylester		E			=		E			=			E			E		
Maleic Anhydride		G			=		E			=			E			E		
Malic Acid, aqueous	50	E			E		G			E			E			E	E	
Malonic Acid Dimethylester		E			=		E			=			E			E		
Manganese Sulphate	Aq	E	G		E	G	E	G		E	G		E	E		E	E	G
Manganese Sulphide		=			E		E	G		E			E	E	G	E	E	G
Manganese Sulphite					E		E	G		E			E	E	G	E	E	G
Manganous Acid							G											
Mercury		E			E		E			E			E	G		E	E	
Mercury ( I ) Chloride	Aq	E			E		E			E			E			E		
Mercury ( I ) Cyanide	Aq						G									E		
Mercury ( I ) Nitrate	Aq	E			E		E			E			E			E		
Mercurous ( II ) Acetate		E			E		E			E			E			E		
Mercurous Chloride		E			E		E			E			E			E		
Mercurous Cyanide							G											
Mercurous Nitrate		E			E		E			E			E			E		
Mercurous ( II ) Sulphide		E			E		G			E			E			E		
Mesityl Oxide		F			=		=			=			E			E	F	
Methacrylic Acid										G								
Methaketone		F											E			E		
Methallyl Alcohol		F			=													
Methanal		G			=		G	=		G	=		E	G		E	E	
Methane		E			F					F			G			E	E	
Methane Acid		E	G		G	=	E	G		E	G		E	G		E	E	
Methanol		F	=		F		E	G		E	G		E	G		E	E	
Methyl Acetate		F			=		=			=			E			E		
Methyl Acetoacetate		F			=		=			=			E			E		
Methyl Acetone		G			=		=			=			E			E		
Methyl Acrylate					=		=			=			E			E		
<b>Corrosiv/ac</b>			<b>Corrosiv/spac</b>															
<b>Carbopomp/1tn</b>			<b>Nafta/16 1tn-tml-tmc</b>															
<b>Corrosiv/hyp</b>			<b>Corrosiv/spl hyp</b>															
<b>Corrosiv/viton</b>			<b>Corrosiv/spl viton</b>															
<b>Corrosiv/cl</b>			<b>Corrosiv/spcl</b>															
<b>Superior hbb</b>			<b>Superior/c hdn</b>									<b>Superior/spl hbb-hdn</b>						

**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data


# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE		
	TEMPERATURE °C																	
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65
Methyl Alcohol	F	=		F			E	G		E	G		E	G		E	E	
Methyl Aldehyde	G			F			G	=		G			E	G		E	E	
Methyl Amine	G			F						F			E			E	E	
Methyl Benzene	=			=			=			E			E			E	=	
Methyl Bromide	G			=			=			E			=			=		
Methyl Butanol	G			F			G			F			E			E		
Methyl Butanone	G			=			=			=			E			E		
Methyl Carbitol				=			=						E			E	E	
Methyl Cellosolve	G			G			=			=			E			E	E	
Methyl Chloride	=			=			=			E			F			G	E	
Methyl Chloroacetate	E			=			=			=			E			E	G	
Methyl Chloroformate	=			=			=			=			G			G	E	
Methyl Cyanide	F			=			F			=			E			E	E	
Methyl Cyclohexane	=			=			=			E			E			E	F	
Methyl Cyclopentane	=			=			=			E			E			E	E	
Methyl Formate	E			=			=			=			G			G	E	
Methyl Glycol	E			E			E			=			E	G		E	E	
Methyl Hexanol				E			E			G			E			E	E	
Methyl Hexanone	=			=			=			=			E			E	E	
Methyl Iodide	E			=			=			=			E			E	E	
Methyl Methacrylate	G			=			E			=			E			E	E	
Methyl Oleate	G			=			=			G			E			E	E	
Methyl Phenol	=			F	=		=			E			E	G	F	E	G	
Methyl Salicylate	G			=			=			=			G			E	E	G
Methyl Styrol	=			=			=			=			E			E	E	
Methyl Allyl Acetate				=			=			=			E			E	E	
Methyl Allyl Chloride				=			=			=			G			E	E	
Methyl Amyl Acetate	G			=			=			=			E			E	E	
Methyl Amyl Alcohol	G			E			=			=			E			E	E	
Methyl Amyl Carbinol				E			G			=			E			E	E	
Methyl Amyl Ketone	G			=			=			=			E			E	E	
Methyl Butyl Ketone	E			=			=			=			E			E	E	
Methyl Dichloroacetate	E			=			=			=			E			E	G	
Methyl Ethyl Ketone ( MEK )	F			=			=			=			E			E	E	
Methyl Glycol Acetate	G			=			F			=			E			E	E	
Methyl Hexyl Ketone	F			=			=			=			E			E	E	
Methyl Isobutyl Carbinol				G			G			G			E			E	E	
Methyl Isobutyl Ketone ( MIBK )	F			=			=			=			E			E	F	
Methyl Isopropyl Ketone	=			=			=			=			E			E	E	
Methyl Propyl Carbinol	G			F			=			=			E			E	E	
<b>Corrosiv/ac</b>			<b>Corrosiv/spac</b>															
<b>Carbopomp/1tn</b>			<b>Nafta/16 1tn-tml-tmc</b>															
<b>Corrosiv/hyp</b>			<b>Corrosiv/spl hyp</b>															
<b>Corrosiv/viton</b>			<b>Corrosiv/spl viton</b>															
<b>Corrosiv/cl</b>			<b>Corrosiv/spcl</b>															
<b>Superior hbb</b>			<b>Superior/c hdn</b>									<b>Superior/spl hbb-hdn</b>						

**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data




# RESISTANCE CHART

		EPDM			NBR1			CSM			FPM			XLPE			UHMWPE		
		TEMPERATURE °C																	
		%																	
		21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65	76
Nickel Nitrate	Aq	E	G		E			E	G		E			E	E	G	E	E	
Nickel Sulphate	Aq	E	G		E	G		E	G		E			E	E	G	E	E	
Nickel Vitriol	Aq	E	G		E	G		E	G		E			E	E	G	E	E	
Nickel Ammonium Sulphate		E			E			E			E			E			E		
Nickel Plating Solutions					F			G						E			E		
Nickelous Chloride		E			E						E			E			E		
Nicotine Bentonite					G									E			E		
Nicotine Salts														E			E		
Nicotine Sulphate		G			G									E			E		
Nitric Acid	10	E	G		=			E	=		E			E			E	E	
Nitric Acid	20	E	G		=			E	=		E			G			E	E	
Nitric Acid	40	G	=		=			E	=		E			F			G	=	
Nitric Acid	60	=			=			F	=		G			=			G		
Nitric Acid	70	=			=			=			F	=		=			G		
Nitric Acid Fuming		=			=			=			F	=		=			=		
Nitrobenzene		=			=			=			=			E	G		E	G	
Nitrogen Gas		E			=			E			E			E			E		
Nitromethane		G			=			=			E			E			E		
Nitrooctane					=									E			E		
Nitropropane		E			=			E			=			E			E		
Nitrogen Tetraoxide		F			=			=			=								
Nitrous Acid	10	F			=			E			=			E			E		
Nitrous Gas		E			=			E			E			E			E		
Nitrous Oxide		E			E			E			E			E			E		
Nitrosyl Chloride					=			=			G			E			E		
Nitrotoluol		=			=			=			E			E			E		
Nonanol		=			E			E			E			E			E	E	
Nonyl Alcohol		=			E			E			E			E			E	E	
4-Nonyl Phenol		=			=			=			E			E			E		
Nonenes		=			E			=			E			E			E		
Octachlorotoluene		=			=			=			E			E			E		
Octadecanoic Acid		E			E	F		F	=		E			E	G		E	G	
Octane		=			E			=			G			E			E		
Octanol		E			E			G			E			E			E		
Octene		=			E						E			=			E		
Octyl Acetate		F			=			=			=			E			E		
Octyl Adipate		F			=			=			=			E			E		
Octyl Alcohol		E			E			G			E			E			E		
Octyl Aldehyde					=			=			=			E			E		
Octyl Amine		G			F			=			=			E			E		
<b>Corrosiv/ac</b>		<b>Corrosiv/spac</b>																	
<b>Carbopomp/1tn</b>		<b>Nafta/16 1tn-tml-tmc</b>																	
<b>Corrosiv/hyp</b>		<b>Corrosiv/spl hyp</b>																	
<b>Corrosiv/viton</b>		<b>Corrosiv/spl viton</b>																	
<b>Corrosiv/cl</b>		<b>Corrosiv/spcl</b>																	
<b>Superior hbb</b>		<b>Superior/c hdn</b>												<b>Superior/spl hbb-hdn</b>					

**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data

# RESISTANCE CHART


	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE		
	TEMPERATURE °C																	
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65
Octyl Carbinol	E			E			E			G			E			E		
Octylene Glycol	E			E			E			E			F			G		
Oil. Petroleum	=			E	G	F	F			E	E	G	E	G		E	G	
Oleic Acid	=			E	F		F	=		G			E	G		E	G	
Oleum	=			=			F			E			=			F		
Oleum Spirits	=			=			=			=			E			E		
Orthodichlorobenzene	=			=			=			G			G			G		
Orthoxylene	=			=			=			E			E			G		
Oxalic Acid	10	E		E			G			E			E	G		E	E	
0-Oxybenzoic Acid		E		E									E			E		
Oxygen		G		=			E			E			E	G		E	E	
Oxytoluene		=		F	=		=			E			E	G	F	E		
Ozone Gas		G		=			E			E			G			G	=	
Paint	Refer to Vehicle or Thinner																	
Paint Oil	Refer to Thinner																	
Palatinol® C	E			=						F			E			E	F	
Palm Oil	G			E			G			E			G			E	E	
Palmitic Acid	G			E	F		F	=		E			G			E	E	
Paper Makers Alum	E			E			E	G		E			E	E	G	E	E	G
Paradichlorobenzene	=			=			=			G			G			G		
Paradichlorobenzol ( Moth Cristals )	=			=			=			G			G			G		
Paraffin	E	G	F	E	G		=			E	G	G	E			E		
Paraffin Oils	=			E			=			E			E			E	E	
Paraformaldehyde	E			G						F			E			E	E	
Paraxylene	=			=			=			E			E			E		
Para San	10												E			E		
Paris Green	37												E			E		
Peanut Oil	=			E			F			E			E			E		
Pelargonic Acid	=			=			=			=			E			E		
Pentachloroethane	=			E			=			E			E			E		
Pentachlorophenol	=			=						E			E			E		
Pentachlorophenol-Kerosene (10%-90%)	=			=						E			E			E		
Pentane	=			E			G			E			E			E		
Pentanone	=			=			=			=			E			E		
Pentanol	G			E			E	E	G	E	E	G	E	G		E	E	
Pentene	=			E			G			E			E			E		
Perchloroethylene	=			=			=			E			E			F		
Perchloric Acid	10	F		=			F			G			E			E	E	
Petrolatum		=		E			E			E			E			E		
<b>Corrosiv/ac</b>			<b>Corrosiv/spac</b>															
<b>Carbopomp/1tn</b>			<b>Nafta/16 1tn-tml-tmc</b>															
<b>Corrosiv/hyp</b>			<b>Corrosiv/spl hyp</b>															
<b>Corrosiv/viton</b>			<b>Corrosiv/spl viton</b>															
<b>Corrosiv/cl</b>			<b>Corrosiv/spcl</b>															
<b>Superior hbb</b>			<b>Superior/c hdn</b>									<b>Superior/spl hbb-hdn</b>						

**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data






# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE			
	TEMPERATURE °C																		
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65	76
Potassium Peroxide Bisulphate	Aq	E			E			E			E			E			E	E	
Producer's Gas		=			E			G			E								
Propane Gas		=			E			E			E			=			E		
Propane Liquid		=			E			=			E			E			E		
Propanediol		E			E			E			E			E			E	E	
Propanetriol		E			E			E			E								
Propanol		E	G		E			E	G		E			G			E	E	
Propanone		G			=			F			=			E			E	E	
Propellor Oil		=												E					
Propenol		E			E			E			E			E			E	E	
Propergol JP1 - JP5		=			E						E			E			E		
Propionic Acid	Aq	E			=			=			E			E			E		
Propion		F			=			=			=			E			E		
Propionitrile					=						=			E			E		
Propyl Acetate		F			=			=			=			E			E		
Propyl Alcohol		E	G		E			E	G		E			G			E	E	
Propyl Aldehyde		F			=			=			=			E			E		
Propyl Amine		F			=			=			=			E			E		
Propyl Chloride		=			=			=			=			G			G		
Propyl Nitrate		G			=			G			=			E			E		
Propylene		=			=			=			=			E			E		
Propylene Diamine		=			F			=			=			E			E		
Propylene Dichloride	99	=			=			=			=			G			=		
Propylene Glycol		E			E			E			E			E			E	E	
Propylene Oxyde		E			=			=			=			E			E	E	
Pydraul Hydraulic Fluids		G			=			=			=			G			G		
Pyranols 1467-1476		=			G			=			=			E			E		
Pyrene		=			=			=			=	G		F			F	=	
Pyridine		F			=			=			=			E			E	G	
Pyroligneous Acid		G						G						E			E		
Pyrolle		=			=			=			=			E			E		
Propionic Acid	Aq	E			=			=			=			E			E		
Quenching Oil														E			E		
Rance Oil														E			E		
Rape Seed Oil		G			G			G			E			G			G		
Red Oil		=			G			G			E			E			E		
Richfield A		=			=			=			=			G			G		
Richfield D	33	=			G						F			G			G		
Rosin Oil											E			E			E		
Rotenone and Water		E			G			E			E			E			E		
<b>Corrosiv/ac</b>		<b>Corrosiv/spac</b>																	
<b>Carbopomp/1tn</b>		<b>Nafta/16 1tn-tml-tmc</b>																	
<b>Corrosiv/hyp</b>		<b>Corrosiv/spl hyp</b>																	
<b>Corrosiv/viton</b>		<b>Corrosiv/spl viton</b>																	
<b>Corrosiv/cl</b>		<b>Corrosiv/spcl</b>																	
<b>Superior hbb</b>		<b>Superior/c hdn</b>												<b>Superior/spl hbb-hdn</b>					


**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data

# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE			
	TEMPERATURE °C																		
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65	76
Round-Up	E			G															
Saccharose	E			E						E				E					E
Salicylic Acid	E			E						E				E				E	E
Sea Water	E	G		E	G					E				E				E	E
Sewage	G			E						E				E	G			E	G
Silica Gel														E				E	
Silicate of Soda	E			E	G			E	G				E	E	G		E	E	G
Silicate Esters	=			G				E					E						
Silicone Grease	E			E	G			E					E				E	E	
Silicone Oils	E			E	G			E					E				E	E	
Silver Azotate	Aq	E		E									E				E		
Silver Cyanide	G							G									E		
Silver Nitrate	Aq	E	G	E				E	G				E				E	E	
Silver Salts	Aq	E		E				E					E				E	E	
Skelly Solvent	=			E				=					=				E		
Skydrol® Hydraulic Fluids	G			=				=					=				E		
Soap Oil				E										E			E		
Soap Solutions	Aq	E	E	G	E	G		E	G	G		E	G	G		E	E	E	E
Soda Ash	E			E	G			E	G				E			E	E	E	
Soda Caustic	20	E	G	G	E	G		E	G	G		E				E	E	E	
Soda Caustic	40	G	G	G	=			E	G	G		E	=			E	E	E	
Soda Caustic	50	G	G	G	=			E	G	G		=				E	E	E	
Soda Caustic	70	=			=			E	G	G		=				E	E	E	
Soda Lime	E			G				G	F				=			E	E	G	E
Soda Niter	E	G		E				E	G				E	G		E	E	G	E
Sodium Acetate	Aq	E		F				=					E			E	E	E	
Sodium Aluminate	Aq	E		E				E					E			E	E	E	
Sodium Benzoate								G									E	E	
Sodium Bicarbonate	Aq	E		E	G			E					E		G		E	E	
Sodium Bichromate	20	G		=				E	G	G			E		E	G	E		
Sodium Biphosphate	Aq			E				G									E		
Sodium Bisulphate	Aq	E		E				E	G				E		E	G	E	E	
Sodium Bisulphide		E		E									E				E		
Sodium Bisulphite	Aq	E		E	G			E	G				E		E	G	E	E	
Sodium Bitartrate		E		E				G					E				E		
Sodium Borate		E		E	G			E					E				E	E	
Sodium Carbonate	Aq	G		E	G			E	G				E		E	G	E	E	
Sodium Chlorate	Aq	E		G	=			E					E				E	E	
Sodium Chloride		E		E	G			E	G				E		E	G	E	E	
Sodium Chlorite	Aq	E		=				E					E				E	E	
<div style="display: flex; justify-content: space-between;"> <span><b>Corrosiv/ac</b></span> <span><b>Corrosiv/spac</b></span> </div>																			
<div style="display: flex; justify-content: space-between;"> <span><b>Carbopomp/1tn</b></span> <span><b>Nafta/16 1tn-tml-tmc</b></span> </div>																			
<div style="display: flex; justify-content: space-between;"> <span><b>Corrosiv/hyp</b></span> <span><b>Corrosiv/spl hyp</b></span> </div>																			
<div style="display: flex; justify-content: space-between;"> <span><b>Corrosiv/viton</b></span> <span><b>Corrosiv/spl viton</b></span> </div>																			
<div style="display: flex; justify-content: space-between;"> <span><b>Corrosiv/cl</b></span> <span><b>Corrosiv/spcl</b></span> </div>																			
<div style="display: flex; justify-content: space-between;"> <span><b>Superior hbb</b></span> <span><b>Superior/c hdn</b></span> <span><b>Superior/spl hbb-hdn</b></span> </div>																			

**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data


# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE			
	TEMPERATURE °C																		
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65	76
Sodium Chromate	G						F	=		E				E			E		
Sodium Cyanide	E			E	G		E	G		E				E	E	G	E	E	
Sodium Ethoxide				G			E			E				E			E		
Sodium Fluoaluminate				E			E			E				E			E		
Sodium Fluoride	E			E			E			E				E			E	E	
Sodium Formate	G						G										E		
Sodium Hydrate	20	E			E		=												
Sodium Hydroxide	20	E	G	G	E	G	E	G	G	E	G			E			E	E	
Sodium Hydroxide	40	G	G	G	=		E	G	G	E	G			E			E	E	
Sodium Hydroxide	50	G	G	G	=		E	G	G	E	G			E			E	E	
Sodium Hydroxide	70	=			=		E	G	G	=				E			E	E	
Sodium Hypochloride	Aq	E			=		E			E				E			E		
Sodium Hypochlorite	5	G	G		=		E	G		E	G			E			E	F	
Sodium Hypochlorite	20	G			=		E	F	=	E	G			E			E	F	
Sodium Hypochlorite	30	G			=		G			G				G			G	F	
Sodium Iodide		E			E		E			E				E			E		
Sodium Methaphosphate	Aq	E			E		G			E				E	G		E		
Sodium Nitrate	Aq	E	G		E		E	G		E	G			E	E	G	E	E	G
Sodium Nitrite	Aq	E			E		E			E				E			E	E	
Sodium Oxalate		E			G		G			E				E			E		
Sodium Perborate	Aq	G	G	G	G	F	E			E				E	G		E	G	
Sodium Perchlorate	Aq	E					G			E				E			E	E	
Sodium Peroxide, aqueous	10	F			G		E	G	G	E				E	G		E	E	
Sodium Phosphate	Aq	E			G		E	G		E				E	E	G	E	E	
Sodium Pyrosulphite		E			E	G	E	G		E				E	E	G	E	E	G
Sodium Silicate	Aq	E			E	G	E	G		E				E	E	G	E	E	G
Sodium Sulphate	Aq	E	G		E	G	E	G		E				E	E	G	E	E	G
Sodium Sulphydrate		E			E		E			E				E			E		
Sodium Sulphide	Aq	E	G		E	G	E	G		E				E	E	G	E	E	G
Sodium Sulphite		E			E		E	G		E				E	E	G	E		
Sodium Thyosulphate	Aq	E			E		E	G		E				E	E	G	E	E	G
Sodium Hydrogen Sulphide	Aq	E			E		E			E				E			E		
Soybean Oil		=			E		=			E				E			E		
Spindle Oil		=			E		=			E							F	F	
Stannic Chloride	Aq	G	F		E		E	G		E	G			E	E	G	E	E	
Stannic Sulphide		E			E		E	G		E				E	E	G	E	E	
Stannous Chloride	15	F			E		E	G	G	E				E	E		E	E	
Stannous Sulphide		E			E		E	G		E				E	E	G	E	E	
Starch	Aq	E			E		E			E				E			E	E	
Steam																			
Use Steam Hoses Only																			
Corrosiv/ac			Corrosiv/spac																
Carbopomp/1tn						Nafta/16 1tn-tml-tmc													
Corrosiv/hyp									Corrosiv/spl hyp										
Corrosiv/viton										Corrosiv/spl viton									
Corrosiv/cl												Corrosiv/spcl							
Superior hbb				Superior/c hdn								Superior/spl hbb-hdn							

**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data




# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE		
	TEMPERATURE °C																	
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65
Tetrabromoethane	=			=			=			E			=			F	=	
Tetrachlorobenzene	=			=			=			G			G			G		
Tetrachloroethane	=			=			=			E			F			F	=	
Tetrachloroethylene	=			=			=			E			F			F	=	
Tetrachloromethane	=			=			=			E	G		F			F	=	
Tetrachloronaphtalene	=			=			=			G			G			G		
Tetrachlorodifluoroethane	=			G						G								
Tetradecanol	E			E			E						E			E		
Tetraethylene Glycol	E			E			E	G		E			E	E	G	E		
Tetrahydrofuran	=			=			=			=			E			E	=	
Tetrahydronaphtalene	=			=			=			E			G			G		
Thionyl Chloride	=			=			=			G			=			=		
Thiophene	=			=			=			E			E			E	=	
Tincal	E			F						E			E			E		
Tin Chloride, aqueous	Aq	G	F	E			E	G		EG			E	E	G	E	E	
Tin Tetrachloride	Aq	G	F	E			E	G		E	G		E	E	G	E	E	
Titanium Tetrachloride	=			=			=			E			G			G		
Toluene	=			=			=			E			E			E		
Toluene Diisocyanate	E						=			F	=							
Toluidine	=			=			=			=			G			G		
Toluol	=			=			=			E			E			E	=	
Toxaphene®	12	=		G									G			G		
Transformer Oils:																		
Petroleum Base	=			G			=			E			E			E		
Chlorinated Phenyl Base Askareis	=			=			=						G			G		
Transmissions Fluids A	=			F	=		=			E			E	G		E	G	
Transmissions Fluids B	=			F	=		=						E			E		
Triacetin	E			E			G			=			E			E		
Tributyl Amine				F			=						E			E		
Tributyl Phosphate	F			=			=			G	F		E			E	E	
Tributoxy Ethyl Phosphate	F			=			=			=								
Trichloroacetic Acid, aqueous	50	G		G			=			E						E	E	
Trichlorobenzene	=			=			=			G			G			G	=	
Trichloroethane	=			=			=			E			E			E		
Trichloroethylene	=			=			=			E			F			G	=	
Trichloroethyl Phosphate ( TCEF )	E			=			E			E			E			E		
Trichloromethane	=			G			E			E			E			E		
Trichloropropane	=			=			=			E			E			E		
Trichlorofluoromethane	=			G			E			E			E			E		
Trichlorotrifluoroethane	=			G			E			E			E			E		
<div style="display: flex; justify-content: space-between;"> <span><b>Corrosiv/ac</b></span> <span><b>Corrosiv/spac</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span><b>Carbopomp/1tn</b></span> <span><b>Nafta/16 1tn-tml-tmc</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span><b>Corrosiv/hyp</b></span> <span><b>Corrosiv/spl hyp</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span><b>Corrosiv/viton</b></span> <span><b>Corrosiv/spl viton</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span><b>Corrosiv/cl</b></span> <span><b>Corrosiv/spcl</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span><b>Superior hbb</b></span> <span><b>Superior/c hdn</b></span> <span><b>Superior/spl hbb-hdn</b></span> </div>																		

**Rating Codes**    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data

# RESISTANCE CHART

	EPDM			NBR1			CSM			FPM			XLPE			UHMWPE		
	TEMPERATURE °C																	
	%	21	65	76	21	65	76	21	65	76	21	65	76	21	38	65	21	65
Tricresyl Phosphate	F			=			=			E	E	G	E			E	E	
Tridecanol				E			E			E			E			E	E	
Triethanolamine	G			F	=		E	G		=			E			E	G	
Triethyl Amine	=			F	=		F			G			E			E		
Triethylene Glycol	E	E		E	G		E	E		E	G		E	E		E	E	
Trimethyl Amine	=			F	=		F			G			E			E		
2-2-4-Trimethyl Amine Pentane	=			E						E			E			G		
Trinitrophenol	E			E	F		E			E			E			F		E
Trinitrotoluene	=			=			G			G			E			=		E
Trioctyl Phosphate	E			=			=			E			E			E		F
Trioxybenzoic Acid	E			E						E			E					
Trioxypropane	E			E	G		E	G	G	E	E	G	E	G		E	G	
Triphenyl Phosphate	G			=			=			F			E			E	E	
Trisodium Phosphate	E			G			E	G		E			E	E	G	E	E	
Trixylil Phosphate	F			=			=			G			E			E	E	
Tung Oil	=			E			E			E			E	G		E	G	
Turbine Oil	=			G			=			E			E			E	E	
Turpentine	=			E			=			E	G		E	G		E	F	
Uconol	E			E						E			E			E	E	
Ucon® Hydrolube Oils	=			E			=			E			E			E	E	
Undecanol	E			E			E			E			G			E	E	
Unsymmetrical Dimethyl Hydrazine	G			F			G						=					
Uran				G			E							E		E	E	
Urea, aqueous	33	E		E			E			E			E			E	E	
Urine		E		E			E			E			E			E	E	
Varnish	=			G			F			E			E			E	E	
Vaseline	=			E			E			E			E			E	E	
Versilube®	E			E			E			E			E			E	E	
Vinegar	G			G			E			E			E	G		E	E	
Vinyl Acetate	E			=			=			=			E	G		E	E	
Vinyl Benzene	=			=			=			E			E	G		E	G	
Vinyl Carbinol	E			E			E			E			E			E	E	
Vinyl Chloride	=			=			=			E			E			=	=	
Vinyl Cyanide	G			=			=			=			E			E	E	
Vinyl Ether	=			=			=			=			E	G		E	G	
Vinyl Fluoride	=			=			=			=			E			E	E	
Vinyl Toluene	=			=			=			E			E			E	E	
Vinyl Trichloride	=			=			=			E			E			E	E	
V.M. and P. Naphta	=			E			=			E			E			=	F	
Vitriol Ether	=			F						=			E			E	E	
<div style="display: flex; justify-content: space-between;"> <span><b>Corrosiv/ac</b></span> <span><b>Corrosiv/spac</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span><b>Carbopomp/1tn</b></span> <span><b>Nafta/16 1tn-tml-tmc</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span><b>Corrosiv/hyp</b></span> <span><b>Corrosiv/spl hyp</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span><b>Corrosiv/viton</b></span> <span><b>Corrosiv/spl viton</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span><b>Corrosiv/cl</b></span> <span><b>Corrosiv/spcl</b></span> </div>																		
<div style="display: flex; justify-content: space-between;"> <span><b>Superior hbb</b></span> <span><b>Superior/c hdn</b></span> <span><b>Superior/spl hbb-hdn</b></span> </div>																		
<b>Rating Codes    E = Excellent    G = Good    F = Fair    = Not Recommended    Blank = Not enough data</b>																		

